

1 Revision 2

2

3 Saltonseaitite, $K_3NaMn^{2+}Cl_6$, the Mn analogue of rinneite from the Salton Sea, California.

4

5 ANTHONY R. KAMPF^{1*}, STUART J. MILLS², FABRIZIO NESTOLA³, MARCO E. CIRIOTTI⁴ AND

6

ANATOLY V. KASATKIN⁵

7

8 ¹Mineral Sciences Department, Natural History Museum of Los Angeles County, 900 Exposition

9

Boulevard, Los Angeles, CA 90007, USA

10 ²Geosciences, Museum Victoria, GPO Box 666, Melbourne 3001, Victoria, Australia

11 ³Department of Geosciences, University of Padua, Via Gradenigo 6, I-35131, Padova, Italy

12 ⁴Associazione Micromineralogica Italiana, via San Pietro 55, I-10073 Devesi-Ciriè, Italy

13 ⁵V/O "Almazjuvelirexport", Ostozhenka str., 22, block 1, 119034 Moscow, Russia

14

*Email: akampf@nhm.org

15

16 Abstract

17 Saltonseaitite, $K_3NaMn^{2+}Cl_6$, is a new mineral from the Salton Sea, Imperial County,

18 California, U.S.A., which formed as the result of the evaporation of geothermal (hydrothermal)

19 brines enriched in K, Na, Mn and Cl. It occurs as lozenge-shaped and bladed crystals to about 10

20 cm that are composites of parallel-grown {012} rhombohedra. It is associated with large, well-

21 formed crystals of sylvite and halite. Crystals are transparent and colorless, but appear light

22 orange due to inclusions of akaganéite. The streak is white and the luster is vitreous to oily, the

23 latter being due to deliquescence. The Mohs hardness is about 2½, the tenacity is brittle, the

24 fracture is irregular, and crystals exhibit one very good cleavage on {110}. The mineral has an
25 astringent taste and is markedly hygroscopic. The measured and calculated densities are 2.26(1)
26 g/cm³ and 2.297 g/cm³, respectively. Saltonseaite is soluble in water at room temperature and
27 crystallizes from solution above 52°C. Optically, saltonseaite is uniaxial positive, with $\omega =$
28 1.577(1) and $\varepsilon = 1.578(1)$ (white light) and is non-pleochroic. Energy dispersive spectroscopic
29 analyses (average of 5) provided: K 28.79, Na 5.35, Mn 13.48, Fe 0.24, Cl 52.19, total 100.05
30 wt%. The empirical formula (based on 6 Cl atoms) is: $\text{K}_{3.00}\text{Na}_{0.95}\text{Mn}^{2+}_{1.00}\text{Fe}^{2+}_{0.02}\text{Cl}_6$. Saltonseaite
31 is trigonal, *R*-3*c*, with cell parameters $a = 12.0966(5)$, $c = 13.9555(10)$ Å, $V = 1768.48(16)$ Å³,
32 and $Z = 6$. The nine strongest lines in the X-ray powder diffraction pattern are [d_{obs} in Å(*I*)(*hkl*)]:
33 5.83(61)(012); 3.498(25)(300); 2.851(68)(131); 2.689(32)(312); 2.625(62)(214);
34 2.542(100)(223); 1.983(32)(324); 1.749(20)(600), and 1.384(22)(multiple). The structure of
35 saltonseaite ($R_1 = 1.08\%$ for 558 $F_o > 4\sigma F$) contains face-sharing chains of alternating Mn²⁺Cl₆
36 octahedra and NaCl₆ polyhedra along *c*. The chains are joined via bonds to eight-coordinated K
37 atoms. Saltonseaite is isostructural with rinneite, K₃NaFe²⁺Cl₆, and very similar in structure with
38 chlormanganokalite, K₄Mn²⁺Cl₆. Existing chemical analyses for saltonseaite and rinneite fail to
39 confirm a solid-solution series between them; experimental studies are needed.

40

41 Keywords: saltonseaite, new mineral, crystal structure, rinneite, chlormanganokalite, evaporite,
42 geothermal brine, Salton Sea, California.

43

44 **Introduction**

45 In May of 1981, California mineral collector/dealer John Seibel collected the world's
46 finest sylvite crystals from along the southern shoreline of the Salton Sea (Imperial County,

47 California). According to a report at that time (Wilson, 1982), the material came from a water-
48 filled pocket about 18 inches (46 cm) beneath the surface crust. The pocket was about 1½ x 20
49 feet (½ x 6 m) in extent and produced about 4,000 lbs. (8,800 kg.) of specimens. John Seibel
50 (personal communication) confirmed those details and provided the approximate location, an
51 evaporite area along the SE shoreline of the Salton Sea near where the New River empties into
52 the Salton Sea (33°07'N 115°41'W). Seibel noted that the site was immediately above a then-
53 active natural hot spring and that, although the area had been diked to inhibit the encroachment of
54 the lake water, the mineralization was clearly of natural origin (this was not a geothermal well).

55 The sylvite crystals from the pocket were colorless to yellow octahedra and cubo-
56 octahedra with lustrous faces, some crystals reaching 8 cm across. Associated with the sylvite
57 were orange-tinted halite cubes up to 10 cm across and bladed masses up to 15 cm across of what
58 was, at the time, tentatively identified by one of the authors (ARK) as rinneite, $K_3NaFeCl_6$, based
59 solely on powder X-ray diffraction. Numerous specimens of the supposed rinneite were sold and
60 presumably still reside in collections around the world.

61 Recently, one of the authors (AVK) reawakened interest in the bladed mineral from this
62 find, suggesting that, based upon its composition, it might represent a new mineral species.
63 Powder X-ray diffraction and semi-quantitative chemical analysis by energy dispersive
64 spectroscopy of material on a small specimen confirmed it to be an analogue of rinneite in which
65 Mn^{2+} replaces Fe^{2+} . Subsequently, crystals on a much larger specimen from the 1981 discovery in
66 the collection of the Natural History Museum of Los Angeles County were also found to be the
67 new mineral. Material from this specimen was used for the characterization of the new mineral.

68 The new species is named saltonseaite in recognition of its discovery just off the southern
69 shoreline of the Salton Sea, Imperial County, California. The new mineral and name have been

70 approved by the Commission on New Minerals, Nomenclature, and Classification of the
71 International Mineralogical Association (IMA 2011-104). The holotype specimen is in the
72 collections of the Natural History Museum of Los Angeles County under catalogue number
73 23604. Fragments of the holotype have also been deposited in the collections of Museum
74 Victoria (Melbourne, Australia) under catalogue number M51615. Saltonseaite is the Mn
75 analogue of rinneite, $K_3NaFeCl_6$. According to group nomenclature (Mills et al. 2009),
76 saltonseaite and rinneite belong to the rinneite group.

77

78 **Occurrence and paragenesis**

79 On the holotype specimen, saltonseaite is associated with sylvite and halite, which occur
80 as well-formed crystals, as granular aggregates of small rounded crystals, and as inclusions in the
81 saltonseaite. Some saltonseaite is partially replaced by sylvite and halite, as evidenced by small
82 equant crystals of these minerals intergrown along the edges of some saltonseaite crystals.
83 Akaganéite commonly occurs as inclusions in the saltonseaite, imparting an orange color.

84 Saltonseaite is an evaporite mineral formed from solutions enriched in K, Na, Mn and Cl.
85 The solutions evidently emanated from a natural hot spring, related to the Salton Sea geothermal
86 field. Robinson et al. (1976) describe the field as follows:

87 The Salton Sea geothermal field lies in the Salton Trough, the landward extension of the
88 Gulf of California, an area of active crustal spreading. The Salton Buttes volcanoes lie
89 within the Salton Sea geothermal field where temperatures measured in wells drilled for
90 geothermal brines range up to 360 degrees C at depths of 1,500 to 2,500 meters
91 (Helgeson, 1968). The wells produce a hot brine containing up to 160,000 ppm of
92 dissolved solids, chiefly Cl, Na, K, Ca, and Fe (White, 1968). Under the influence of this

93 hot saline brine, the sediments of the Salton Trough are being transformed into
94 metamorphic rocks of the greenschist facies (Muffler and White, 1969).
95 McKibben et al. (1987) provide a review of research on the geochemistry and distribution of the
96 brines in the Salton Sea geothermal system (SSGS). They note that “Deep geothermal fluids
97 produced from SSGS wells are mainly Na-Ca-K-Fe-Mn-Cl brines.” They further provide the
98 following overview of the genesis of the fluids:

99 Metallogenesis in the Salton Sea geothermal system is caused by the unique coincidence
100 of several geologic and tectonic factors: trans-axial entry of a major river into an active
101 continental rift-zone, deposition of metal-bearing deltaic sediments to form a closed-basin
102 sedimentary environment, saline basin waters built up by episodic lake-filling and
103 evaporite formation, and injection of heat and elements by rift-related magmatic
104 intrusions at depth. These processes lead to leaching of metals and salt from the deltaic-
105 lacustrine host sediments and the formation of hot hypersaline brines, which rise
106 diapirically to mix with shallow oxidized waters and deposit hydrothermal ore minerals.

107 It is worth noting that the formation of saltonseaitite from a brine related to a magmatic system
108 provides an interesting parallel to one of the occurrences of rinneite and to the only occurrence of
109 chlormanganokalite, $K_4Mn^{2+}Cl_6$, in sublimates on Mt. Vesuvius, Italy.

110

111 **Physical and optical properties**

112 Saltonseaitite occurs as lozenge-shaped and bladed crystals (Figs. 1 and 2) to about 10 cm
113 that are composites of parallel-grown {012} rhombohedra (Fig. 3). Crystals are colorless, but
114 typically appear light orange due to inclusions of akaganéite. The streak is white. Crystals are
115 transparent with vitreous to oily luster, the latter being due to deliquescence. Saltonseaitite does

116 not fluoresce in long or short wave ultraviolet light. The Mohs hardness is about 2½, the tenacity
117 is brittle, the fracture is irregular, and crystals exhibit one very good cleavage on {110}. The
118 mineral has an astringent taste and is markedly hygroscopic. The density measured using a
119 Berman balance is 2.26(1) g/cm³, but this is likely to be low because of inclusions of sylvite and
120 halite. The calculated density based on the empirical formula and the unit cell refined from the
121 single-crystal data is 2.297 g/cm³. Saltonseaite readily dissolves in water at room temperature.
122 Upon heating an aqueous solution in which saltonseaite has been dissolved, the phase begins to
123 crystallize above 52°C. Optically, saltonseaite is uniaxial positive, with $\omega = 1.577(1)$ and $\varepsilon =$
124 $1.578(1)$, measured in white light. The mineral is non-pleochroic.

125

126 **Chemical composition**

127 Early attempts to prepare samples and conduct electron microprobe analyses in two
128 different laboratories provided very poor results because of the very hygroscopic nature of the
129 mineral. Energy dispersive spectroscopic analysis was found to be less affected by adsorbed
130 surface water. To further mitigate sample deterioration, after mounting crystals in epoxy resin,
131 polishing was conducted using a ligroin (petroleum ether).

132 Chemical analyses (5 points on two crystals) were carried out on crystals from the
133 holotype specimen using a Stereoscan S360 Cambridge electron microscope with an Oxford
134 Instruments INCA analyzer energy dispersive X-ray spectrometer, equipped with a Link Pentafet
135 SATW detector. The working conditions were: 15 kV accelerating voltage, 1.5 nA beam current,
136 2.0 μm beam dimension and 100 s live-time. The standards used were MAD-10 Feldspar (for K),
137 albite (for Na), Mn metal (for Mn), Fe metal (for Fe), and KCl (for Cl). Other elements were
138 looked for, but were found to be below detection limits. The INCA software processed the data

139 based upon Cl by stoichiometry and provided the analyses reported in Table 1. The empirical
140 formula (based on 6 Cl atoms) is $K_{3.00}Na_{0.95}Mn^{2+}_{1.00}Fe^{2+}_{0.02}Cl_6$. The simplified formula is
141 $K_3NaMn^{2+}Cl_6$, which requires K 28.75, Na 5.64, Mn 13.47, Cl 52.14, total 100.00 wt%.

142 The Gladstone-Dale compatibility index $1 - (K_p/K_C)$ as defined by Mandarino (1981)
143 provides a measure of the consistency among the average index of refraction, calculated density,
144 and chemical composition. For saltonseaitite, the compatibility index is 0.028 based on the ideal
145 formula, within the range of excellent compatibility.

146

147 **X-ray crystallography and structure refinement**

148 Both powder and single-crystal X-ray studies were carried out using a Rigaku R-Axis
149 Rapid II curved imaging plate microdiffractometer, with monochromatized $MoK\alpha$ radiation. For
150 the powder-diffraction study, a Gandolfi-like motion on the φ and ω axes was used to randomize
151 the sample and observed d -spacings and intensities were derived by profile fitting using JADE
152 9.3 software. The powder data are presented in Table 2. Unit-cell parameters refined from the
153 powder data using whole pattern fitting are: $a = 12.103(4)$, $c = 13.979(5)$ Å, and $V = 1773.3(1.0)$
154 Å³.

155 The Rigaku CrystalClear software package was used for processing the structure data,
156 including the application of an empirical multi-scan absorption correction using ABSCOR
157 (Higashi 2001). The initial atomic positions were based upon those in the structure determination
158 of rinneite (Figgis et al. 2000). SHELXL-97 software (Sheldrick 2008) was used, with neutral
159 atom scattering factors, for the refinement of the structure. The details of the data collection and
160 the final structure refinement are provided in Table 3. The final fractional coordinates and atom

161 displacement parameters are provided in Table 4. Selected interatomic distances are listed in
162 Table 5 and bond valences in Table 6.

163

164 **Description of the structure**

165 The structure of saltonseaitite (Fig. 4) contains face-sharing chains of alternating $\text{Mn}^{2+}\text{Cl}_6$
166 octahedra and NaCl_6 polyhedra along **c**. The chains are joined via bonds to eight-coordinated K
167 atoms. The MnCl_6 octahedron has close to ideal geometry, with all Mn–Cl bond distances equal
168 and all octahedral angles between 88.2 and 91.8°. The NaCl_6 polyhedron also has six equivalent
169 cation–anion bond distances; however, to accommodate the longer Na–Cl bonds and the
170 opposing faces shared with MnCl_6 octahedra, the NaCl_6 polyhedron is severely elongated. The
171 NaCl_6 coordination polyhedron can be considered an elongated octahedron, but it is probably
172 better described as twisted trigonal prism. The shape of the KCl_8 coordination polyhedron is not
173 easily described, but the K–Cl bonds fall within a fairly narrow range, 3.202 to 3.355 Å. The Cl
174 is coordinated to one Mn, one Na and four K atoms in an approximately octahedral arrangement.

175 Saltonseaitite is isostructural with rinneite, $\text{K}_3\text{NaFe}^{2+}\text{Cl}_6$ (Beattie and Moore 1982; Figgis
176 et al. 2000), and very similar in structure with chlormanganokalite, $\text{K}_4\text{Mn}^{2+}\text{Cl}_6$ (Bellanca 1947a,
177 1947b). The structure of chlormanganokalite was originally described using the trigonal
178 rhombohedral cell with parameters $a = 8.468$ Å and $\alpha = 89.53^\circ$, which corresponds to the non-
179 primitive hexagonal cell with cell parameters $a = 11.926$ and $c = 14.787$ Å. The much longer *c*
180 cell dimension for chlormanganokalite compared to saltonseaitite and rinneite is particularly
181 significant as it reflects a KCl_6 polyhedron in the face-sharing chain that is much more severely
182 elongated than the NaCl_6 polyhedron in the chains in saltonseaitite and rinneite. As a consequence,

183 the K atoms linking the chains in chlormanganokalite are six-coordinated, rather than eight-
184 coordinated, as they are in saltonseaite and rinneite.

185 The Mn–Cl bond length of 2.55311(19) Å in saltonseaite is significantly longer than, but
186 comparable to, the Fe–Cl bond length of 2.5124(5) Å in rinneite (Figgis et al., 2000). This raises
187 the question of whether a complete, or even a limited, solid solution series exists between
188 saltonseaite and rinneite. Existing evidence is limited to the published chemical analyses for
189 rinneite from evaporite deposits (Eskdale, North Yorkshire, England; Wolkramshausen,
190 Thuringia, Germany; and Hildesheim, Lower Saxony, Germany), which at most show only a
191 trace of Mn (0.18 wt% for Eskdale; Stewart, 1951), and our analyses for saltonseaite, which show
192 only a trace of Fe (0.24 wt%). The fact that rinneite analyses exhibit little or no Mn could simply
193 be due to the low abundance of Mn in the solutions that formed the evaporite deposits in which
194 the rinneite occurs. Interestingly, rinneite has also been reported from a single 1922 discovery in
195 a fumarole at Mt. Vesuvius (Zambonini and Restaino, 1924); however, there are no published
196 chemical analyses of this material. The very low Fe content of saltonseaite may be more telling,
197 because Fe is known to be enriched in fluids in the Salton Sea geothermal system (Robinson et
198 al., 1976; McKibben et al., 1987). The presence of akaganéite, Fe³⁺O(OH), as inclusions in
199 saltonseaite, further confirms the presence of Fe in the solution from which saltonseaite
200 crystallized; however, the lack of greater incorporation of Fe into the saltonseaite structure could
201 be attributable to crystallization under moderately oxidizing conditions in which most Fe was
202 present as Fe³⁺, but Mn was present as Mn²⁺. Experimental studies are clearly needed to
203 determine the extent of the solid solution series between saltonseaite and rinneite.

204

205 **Acknowledgements**

206 Reviewers William S. Wise and Paula C. Piilonen and associate editor Fernando Colombo are
207 thanked for their constructive comments on the manuscript. This study was funded by the John
208 Jago Trelawney Endowment to the Mineral Sciences Department of the Natural History Museum
209 of Los Angeles County.

210

211 **References**

212 Beattie, J.K. and Moore, C.J. (1982) Crystal and molecular structures of rinneite, sodium
213 tripotassium hexachloroferrate(II), and hexaamminecobalt(III) hexachloroferrate(III).
214 Comparison of iron-chloride distances in hexachloroferrates(II) and -(III). *Inorganic*
215 *Chemistry*, 21, 1292–1295.

216 Bellanca, A. (1947a) La struttura della cloromanganocalite. *Periodico di Mineralogia*, 16, 73–88
217 (in Italian).

218 Bellanca, A. (1947b) La rinneite: struttura e relazioni cristallografiche con la
219 cloromanganocalite. *Periodico di Mineralogia*, 16, 199–213 (in Italian).

220 Brese, N.E. and O’Keeffe, M. (1991) Bond-valence parameters for solids. *Acta*
221 *Crystallographica*, B47, 192–197.

222 Brown, I.D. and Altermatt, D. (1985) Bond-Valence Parameters Obtained from a Systematic
223 Analysis of the Inorganic Crystal Structure Database. *Acta Crystallographica*, B41, 244–247.

224 Figgis, B.N., Sobolev, A.N., Kucharski E.S., and Broughton, V. (2000) Rinneite, $K_3Na[FeCl_6]$, at
225 293, 84 and 9.5 K. *Acta Crystallographica*, C56, e228–e229.

226 Helgeson, H.C. (1968) Geologic and thermodynamic characteristics of the Salton Sea geothermal
227 system. *American Journal of Science*, 266, 129–166.

228 Higashi, T. (2001) *ABSCOR*. Rigaku Corporation, Tokyo, Japan.

- 229 Mandarin, J.A. (1981) The Gladstone-Dale relationship: Part IV. The compatibility concept and
230 its application. *Canadian Mineralogist*, 19, 441–450.
- 231 McKibben, M.A., Williams, A.E., Elders, W.A., and Eldridge, C.S. (1987) Saline brines and
232 metallogenesis in a sediment-filled rift: The Salton Sea geothermal system, California.
233 *Applied Geochemistry*, 2, 563–578.
- 234 Mills, S.J., Hatert, F., Nickel, E.H. and Ferraris, G. (2009) The standardisation of mineral group
235 hierarchies: application to recent nomenclature proposals. *European Journal of Mineralogy*,
236 21, 1073–1080.
- 237 Muffler, L.J.P. and White, D.E. (1969) Active Metamorphism of Upper Cenozoic Sediments in
238 the Salton Sea Geothermal Field and the Salton Trough, Southeastern California. *Geological*
239 *Society of America Bulletin*, 80, 157–182.
- 240 Stewart, F.H. (1951) The petrology of the evaporites of the Eskdale no. 2 boring, east Yorkshire.
241 *Mineralogical Magazine*, 29, 557–572.
- 242 Robinson, P.T., Elders, W.A., and Muffler, L.J.P. (1976) Quaternary volcanism in the Salton Sea
243 geothermal field, Imperial Valley, California. *Geological Society of America Bulletin*, 87,
244 347–360.
- 245 Sheldrick, G.M (2008) A short history of SHELX. *Acta Crystallographica*, A64, 112–122.
- 246 White, D.E. (1968) Environments of generation of some base-metal ore deposits. *Economic*
247 *Geology*, 63, 301–335.
- 248 Wilson, W.E. (1982) What's New in Minerals? *Mineralogical Record*, 13, 39–42.
- 249 Zambonini, F. and Restaino, S. (1924) Sulla presenza di cloruro ferroso fra i prodotti dell'attuale
250 attività del Vesuvio. *Annali del Reale Osservatorio Vesuviano*, serie 3, 1, 121–126 (in
251 Italian).
- 252

253

FIGURE CAPTIONS

254 Figure 1. Holotype specimen of saltonseaite, 22 cm tall. (color online)

255 Figure 2. Composite blades of saltonseaite associated with halite crystals on the holotype
256 specimen; FOV 5 cm across. (color online)

257 Figure 3. Crystal drawing demonstrating how the large lozenge-shaped and bladed crystals of
258 saltonseaite are composites of parallel-grown rhombohedra (clinographic projection in
259 standard orientation).

260 Figure 4. Crystal structure of saltonseaite. MnCl_6 octahedra are dark gray (orange online). NaCl_6
261 polyhedra are light gray (yellow online). K atoms shown as dark gray spheres (blue
262 online).

263

264 Table 1. Analytical results (in wt%) for saltonseaite.
265

	1	2	3	4	5	average	S.D.
K	28.82	29.10	29.02	28.70	28.33	28.79	0.27
Na	5.23	5.14	5.35	5.20	5.85	5.35	0.26
Mn	13.79	13.67	13.28	13.41	13.25	13.48	0.21
Fe	0.04	0.07	0.42	0.20	0.45	0.24	0.17
Cl	52.02	52.01	52.14	52.40	52.37	52.19	0.17
Total	99.90	99.99	100.21	99.91	100.25	100.05	

266
267

Table 2. Powder X-ray diffraction data for saltonseaitte.*

I_{obs}	d_{obs}	d_{calc}	I_{calc}	$h k l$	I_{obs}	d_{obs}	d_{calc}	I_{calc}	$h k l$
14	6.084(7)	6.0483	27	1 1 0	9	1.7811(18)	1.7962	2	0 5 4
61	5.831(5)	5.8074	45	0 1 2			1.7807	3	2 1 7
4	4.187(7)	4.1890	3	2 0 2	20	1.7486(3)	1.7460	20	6 0 0
3	3.814(5)	3.8092	5	2 1 1	6	1.7246(5)	1.7219	1	2 4 4
18	3.693(3)	3.6874	11	1 1 3			1.7207	7	0 1 8
25	3.4980(12)	3.4920	23	3 0 0	12	1.6786(5)	1.6775	7	5 2 0
10	3.325(2)	3.3101	9	1 0 4			1.6721	4	3 4 2
5	3.040(4)	3.0242	6	2 2 0	14	1.6479(7)	1.6551	2	2 0 8
13	2.9107(9)	2.9037	19	0 2 4			1.6439	11	1 3 7
68	2.8509(4)	2.8445	60	1 3 1			1.6304	3	1 4 6
32	2.6886(9)	2.6823	30	3 1 2			1.5964	1	1 2 8
62	2.6250(8)	2.6177	56	2 1 4	9	1.5899(6)	1.5872	7	1 6 1
100	2.5424(4)	2.5355	100	2 2 3			1.5780	2	2 5 3
6	2.3700(14)	2.3685	5	3 2 1	4	1.5623(5)	1.5601	4	1 5 5
16	2.3344(11)	2.3259	10	0 0 6			1.5573	2	6 1 2
16	2.2873(7)	2.2860	8	4 1 0	5	1.5368(8)	1.5344	5	3 2 7
		2.2813	8	1 2 5	3	1.5065(8)	1.5020	2	1 1 9
		2.2723	3	2 3 2	3	1.4662(7)	1.4633	6	5 3 2
11	2.2379(10)	2.2327	9	1 3 4	5	1.4402(15)	1.4449	1	6 2 1
7	2.1774(9)	2.1709	6	1 1 6			1.4380	3	4 4 3
4	2.099(4)	2.0945	3	4 0 4			1.4223	1	2 6 2
		2.0517	2	1 4 3	8	1.4105(13)	1.4118	3	2 3 8
5	2.0153(19)	2.0161	5	3 3 0			1.4048	2	2 4 7
		2.0128	2	3 1 5			1.3963	2	0 6 6
32	1.9829(5)	1.9792	30	3 2 4			1.3865	6	6 1 5
		1.9358	3	3 0 6	22	1.3841(7)	1.3833	3	1 0 10
4	1.907(7)	1.9046	3	4 2 2			1.3798	2	2 2 9
7	1.8691(7)	1.8647	8	5 1 1			1.3754	12	3 5 4
12	1.8470(8)	1.8437	10	2 2 6	7	1.3428(6)	1.3411	2	6 2 4
3	1.8219(6)	1.8212	1	2 3 5			1.3406	5	5 0 8
		1.8167	4	1 5 2	4	1.3194(15)	1.3189	1	5 3 5
							1.3172	2	4 5 2

*Only calculated lines with intensities greater than 2 are listed unless they correspond to observed lines.

273 Table 3. Data collection and structure refinement details for saltonseaito.
 274

275	Diffractometer	Rigaku R-Axis Rapid II
276	X-ray radiation / power	MoK α ($\lambda = 0.71075 \text{ \AA}$)
277	Temperature	298(2) K
278	Structural Formula	K ₃ NaMnCl ₆
279	Space group	<i>R</i> -3 <i>c</i>
280	Unit cell dimensions	<i>a</i> = 12.0966(5) \AA
281		<i>c</i> = 13.9555(10) \AA
282	<i>V</i>	1768.48(16) \AA^3
283	<i>Z</i>	6
284	Density (for above formula)	2.300 g/cm ³
285	Absorption coefficient	3.513 mm ⁻¹
286	<i>F</i> (000)	1170
287	Crystal size	230 × 160 × 150 μm
288	θ range	4.87 to 30.48°
289	Index ranges	-17 ≤ <i>h</i> ≤ 17, -17 ≤ <i>k</i> ≤ 17, -19 ≤ <i>l</i> ≤ 19
290	Reflections collected / unique	7087/585 [<i>R</i> _{int} = 0.0197]
291	Reflections with <i>F</i> _o > 4 σ <i>F</i>	558
292	Completeness to $\theta = 30.48^\circ$	97.2%
293	Max. and min. transmission	0.6208 and 0.4988
294	Refinement method	Full-matrix least-squares on <i>F</i> ²
295	Parameters refined	19
296	GoF	1.115
297	Final <i>R</i> indices [<i>F</i> _o > 4 σ <i>F</i>]	<i>R</i> ₁ = 0.0108, w <i>R</i> ₂ = 0.0245
298	<i>R</i> indices (all data)	<i>R</i> ₁ = 0.0117, w <i>R</i> ₂ = 0.0247
299	Largest diff. peak / hole	+0.19 / -0.21 <i>e</i> \AA^{-3}

300
 301 Notes: $R_{\text{int}} = \Sigma|F_o^2 - F_o^2(\text{mean})| / \Sigma[F_o^2]$. $\text{GoF} = S = \{\Sigma[w(F_o^2 - F_c^2)^2] / (n-p)\}^{1/2}$. $R_1 = \Sigma||F_o| - |F_c|| / \Sigma|F_o|$.
 302 $wR_2 = \{\Sigma[w(F_o^2 - F_c^2)^2] / \Sigma[w(F_o^2)^2]\}^{1/2}$. $w = 1 / [\sigma^2(F_o^2) + (aP)^2 + bP]$ where *a* is 0.0110, *b* is 0.7260
 303 and *P* is $[2F_c^2 + \text{Max}(F_o^2, 0)] / 3$.

304

305 Table 4. Fractional coordinates and equivalent atomic displacement parameters (\AA^2) for saltonseaito.
306

307		x/a	y/b	z/c	U_{eq}	U_{11}	U_{22}	U_{33}	U_{23}	U_{13}	U_{12}
308	K	0.29052(2)	0.3333	0.0833	0.02685(7)	0.02627(9)	0.02558(12)	0.02846(12)	-0.00548(8)	-0.00274(4)	0.01279(6)
309	Na	0.0000	0.0000	0.2500	0.02882(17)	0.0344(3)	0.0344(3)	0.0178(3)	0.000	0.000	0.01718(13)
310	Mn	0.0000	0.0000	0.0000	0.01644(6)	0.01713(8)	0.01713(8)	0.01504(11)	0.000	0.000	0.00857(4)
311	Cl	0.181550(17)	0.027130(18)	0.108876(12)	0.02324(6)	0.02080(9)	0.02933(10)	0.02162(9)	-0.00062(6)	-0.00331(6)	0.01406(7)

312

313 Table 5. Selected bond distances (Å) in saltonseite.

314

315	K–Cl (×2)	3.2021(2)	Na–Cl (×6)	2.8441(2)
316	K–Cl (×2)	3.2093(3)		
317	K–Cl (×2)	3.2713(2)	Mn–Cl (×6)	2.55311(19)
318	K–Cl (×2)	3.3555(3)		
319	< K–Cl >	3.2596		

320

321

322 Table 6. Bond-valence summations for saltonseite.

323

	K	Na	Mn	Σ
Cl	0.158 ×2↓ 0.155 ×2↓ 0.131 ×2↓ 0.104 ×2↓	0.153 ×6↓	0.321 ×6↓	1.022
Σ	1.096	0.918	1.926	

324

325 *Notes:* Multiplicity is indicated by ×↓; K–Cl and Mn²⁺–Cl bond strength from Brown and
 326 Altermatt (1985); Na–Cl bond strength from Brese and O’Keeffe (1991).

327







