

Mn³⁺ and the pink color of gem-quality euclase from northeast Brazil

**LÆTITIA GILLES-GUÉRY^{1,†}, LAURENCE GALOISY^{1,*}, JURGEN SCHNELLRATH², BENOIT BAPTISTE¹, AND
GEORGES CALAS^{1,‡}**

¹Sorbonne Université, Muséum National d'Histoire Naturelle, CNRS, IRD, Institut de Minéralogie, de Physique des Matériaux et de Cosmochimie (IMPMC), 4 Place Jussieu 75252 Paris Cedex 05 Paris, France

²Centro de Tecnologia Mineral (CETEM), Ilha da Cidade Universitária, 21.941-908 Rio de Janeiro, RJ, Brazil

ABSTRACT

Pink euclase of gem quality and centimeter size, presenting an unusual pink-orange coloration and a pink to orange pleochroism, was discovered near Livramento de Nossa Senhora, in Bahia State, Brazil. The origin of the pink coloration has been investigated using several spectroscopic techniques: UV-Vis-NIR spectroscopy, electron paramagnetic resonance (EPR), luminescence, and X-ray absorption near edge structure (XANES). The coloration is mainly due to the presence of Mn³⁺ substituted to octahedral Al³⁺ that causes an intense split band at about 18 500 and 21 000 cm⁻¹. The crystal field splitting D_q , crystal field stabilization energy (CFSE), and Racah parameter B for Mn³⁺ are 2055.5 cm⁻¹, 147 kJ/mol, and 886 cm⁻¹, respectively. The Mn³⁺ molar extinction coefficient varies as a function of polarization, between 23 and 55 L·mol⁻¹·cm⁻¹. An additional absorption band, near 24 000 cm⁻¹, together with the rising background toward the UV, tentatively assigned to the O → Fe³⁺ OMCT, contributes to the pink-orange hue. The in-situ UV-Vis-NIR spectra on heating up to 500 °C show a color change toward an intense, stable pink color. CIE colorimetric parameters demonstrate that the color of the investigated euclase remains in the pink domain before and after heat treatment. In the absence of Mn²⁺, shown by EPR and luminescence, the presence of Mn³⁺ evidences oxidative formation conditions due to contamination of the hydrothermal fluids by the surrounding host rock.

Keywords: Euclase, manganese, pink color, optical spectroscopy, crystal field, heat treatment, pleochroism, gems