

High-pressure phase transformation in $\text{LiFeGe}_2\text{O}_6$ pyroxene

FABRIZIO NESTOLA,^{1,*} GÜNTHER J. REDHAMMER,² MARTHA G. PAMATO,¹ LUCIANO SECCO,¹ AND ALBERTO DAL NEGRO¹

¹Dipartimento di Geoscienze, Università di Padova, Via Giotto 1, I-35135 Padova, Italy

²Department of Materials Engineering and Physics, Division of Mineralogy, University of Salzburg, Hellbrunnerstr, 34, 24 A-5020 Salzburg, Austria

ABSTRACT

A synthetic pyroxene with composition $\text{LiFeGe}_2\text{O}_6$ and space group $P2_1/c$ at ambient conditions was investigated by single-crystal X-ray diffraction using a diamond anvil cell. The unit-cell parameters and crystal structure were determined at eight different pressures up to 8.7 GPa. Between 4.16 and 4.83 GPa, the sample shows a strongly first-order phase transition as indicated by a drastic drop in a , c , β , and unit-cell volume. The transition is marked by the disappearance of b -type reflections ($h + k = \text{odd}$) forbidden in a C -centered lattice. The volume bulk modulus of the $P2_1/c$ phase is estimated to be 110 GPa as compared to 147 GPa of the $C2/c$ one. The crystal structure evolution as a function of pressure is mainly influenced by the kinking of tetrahedral chains; the A and B non-symmetry equivalent chains of the $P2_1/c$ phase undergo strong deformations up to 4.16 GPa (A chain $\sim 2\%$, B chain $\sim 5.3\%$). At the transition, the two chains become symmetry equivalent and the single tetrahedral chain of the $C2/c$ phase shows only minor deformations with pressure ($\sim 1.9\%$) due to its already strong kinking ($\sim 130^\circ$). Such behavior is the main reason for the strong difference in compressibility between the low- and high-symmetry forms.

Keywords: Single-crystal structure analysis, germanates, high-pressure phase transformations, X-ray diffraction