

A crystal-chemical investigation of clinozoisite synthesized along the join $\text{Ca}_2\text{Al}_3\text{Si}_3\text{O}_{12}(\text{OH})$ - $\text{Ca}_2\text{Al}_2\text{CrSi}_3\text{O}_{12}(\text{OH})$

MARIKO NAGASHIMA,^{1,2,*} CHARLES A. GEIGER,¹ AND MASAHIDE AKASAKA³

¹Institut für Geowissenschaften, Abteilung Mineralogie, Christian-Albrechts-Universität zu Kiel, D-24098 Kiel, Germany

²Mineralogical Crystallography, Institute of Geological Sciences, University of Bern, Freiestrasse 3, CH-3012 Bern, Switzerland

³Department of Geoscience, Faculty of Science and Engineering, Shimane University, Matsue 690-8504, Japan

ABSTRACT

Cr³⁺-bearing clinozoisite along the join $\text{Ca}_2\text{Al}_3\text{Si}_3\text{O}_{12}(\text{OH})$ - $\text{Ca}_2\text{Al}_2\text{Cr}^{3+}\text{Si}_3\text{O}_{12}(\text{OH})$ was synthesized using cold-seal pressure vessels at $P_{\text{H}_2\text{O}} = 0.35$ to 0.40 GPa and $T = 500$ °C and a piston-cylinder apparatus at $P_{\text{H}_2\text{O}} = 0.8$ to 1.5 GPa and $T = 500$ to 800 °C. Gel-starting materials of $\text{Ca}_2\text{Al}_{3-q}\text{Cr}_q^{3+}\text{Si}_3\text{O}_{12.5}$ composition with $q = 1.00, 0.75, 0.50,$ and 0.25 were employed to maximize the yields of clinozoisite. Mass fractions of clinozoisite in the experimental products with $q = 0.50, 0.75,$ and 1 were about 70 to 90% along with lesser amounts of eskolaite, garnet, and quartz. Clinozoisite crystallized from the gel with $q = 0.25$ was associated only with zoisite. The crystal structures of clinozoisite in four runs, containing 0.28, 0.49, 0.50, and 0.62 Cr apfu were refined using X-ray powder diffraction data and the Rietveld method. The amount of Cr³⁺ at the octahedral M3 and M1 sites ranged from 0.37(1)–0.16(1) to 0.25(1)–0.12(1) apfu, respectively. Corresponding $K_D = (\text{Cr}^{3+}/\text{Al})^{\text{M1}}/(\text{Cr}^{3+}/\text{Al})^{\text{M3}}$ values range between 0.57 and 0.73. The M2 site contained only Al. The K_D values, and published results for intracrystalline partitioning in epidote and piemontite, show that the preference of Cr³⁺ for M1 is stronger than that of Fe³⁺ and Mn³⁺ in spite of the fact that most Cr³⁺ is partitioned into M3. Unit-cell parameters of clinozoisite increase with increasing Cr³⁺. Variations in macroscopic unit-cell parameters can be related to variations in the local M3-O_i and M1-O_i distances.

Keywords: Clinozoisite, zoisite, chromium, synthesis, crystal chemistry, Rietveld refinement