

## Probing the site occupancies of Co-, Ni-, and Mn-substituted biogenic magnetite using XAS and XMCD

VICTORIA S. COKER,<sup>1,\*</sup> CAROLYN I. PEARCE,<sup>1</sup> RICHARD A.D. PATTRICK,<sup>1</sup> GERRIT VAN DER LAAN,<sup>1,2,3</sup>  
NEIL D. TELLING,<sup>2</sup> JOHN M. CHARNOCK,<sup>1</sup> ELKE ARENHOLZ,<sup>4</sup> AND JONATHAN R. LLOYD<sup>1</sup>

<sup>1</sup>School of Earth, Atmospheric and Environmental Sciences and Williamson Research Centre for Molecular Environmental Science, University of Manchester, Manchester M13 9PL, U.K.

<sup>2</sup>Magnetic Spectroscopy Group, Daresbury Laboratory, Warrington WA4 4AD, U.K.

<sup>3</sup>Diamond Light Source, Chilton, Didcot OX11 0DE, U.K.

<sup>4</sup>Advanced Light Source, Lawrence Berkeley National Laboratory, Berkeley, California 94720, U.S.A.

### ABSTRACT

Ferrimagnetic nanoparticles have many uses in industry including in magnetic recording media and transformers, however these particles are often expensive to synthesize. In this study, the Fe<sup>3+</sup>-reducing bacteria *Geobacter sulfurreducens* and *Shewanella oneidensis* were used to synthesize spinel ferrite nanoparticles of the general chemical formula  $M_x\text{Fe}_{3-x}\text{O}_4$ , where  $M$  is either Co, Ni, Mn, Zn, or a combination of Mn and Zn. This was done at ambient temperatures through the dissimilatory reduction of Fe<sup>3+</sup>-oxyhydroxides containing the appropriate substitutional cations. A combination of  $L$ -edge and  $K$ -edge X-ray absorption spectroscopy (XAS) and  $L$ -edge X-ray magnetic circular dichroism (XMCD) was used to determine the site occupancies, valence, and local structure of the Fe and substitutional cations within the spinels. The Ni and Co ferrites produced using each bacterium were very similar and therefore this study concludes that, despite the difference in reduction mechanism of the bacteria used, the end-product is remarkably unaltered. Nickel ferrites contained only Ni<sup>2+</sup>, with at least 80% in O<sub>h</sub> coordination. Cobalt ferrites contained only Co<sup>2+</sup> but with a significant proportion (up to 45%) in T<sub>d</sub> coordination, showing a slight preference for T<sub>d</sub> sites. The Mn-ferrites contained Mn<sup>2+</sup> only on the O<sub>h</sub> sites but a mixture of Mn<sup>2+</sup> and Mn<sup>3+</sup> on T<sub>d</sub> sites when the amount of Mn exceeded 3% (compared to the amount of Fe) or some Zn was also present. This study successfully produced a range of nanoparticulate ferrites that could be produced industrially using relatively environmentally benign methodologies.

**Keywords:** Magnetite, Fe<sup>3+</sup>-reducing bacteria, substituted spinels, *Geobacter sulfurreducens*, *Shewanella oneidensis*, nanotechnology