

## **Principles of thermal expansion in the feldspar system**

**GUY L. HOVIS,\* AARON MEDFORD, MARICATE CONLON, ALLISON TETHER,  
AND ANTHONY ROMANOSKI**

Department of Geology and Environmental Geosciences, Lafayette College, Easton, Pennsylvania 18042, U.S.A.

### **ABSTRACT**

Following the recent thermal expansion work of Hovis et al. (2008) on  $\text{AlSi}_3$  feldspars, we have investigated the thermal expansion of plagioclase, Ba-K, and Ca-K feldspar crystalline solutions. X-ray powder diffraction data were collected between room temperature and 925 °C on six natural plagioclase specimens ranging in composition from anorthite to oligoclase (and as well on their K-exchanged equivalents) and five synthetic Ba-K feldspars with compositions from 25 to 99 mol%  $\text{BaAl}_2\text{Si}_2\text{O}_8$ . The resulting thermal expansion coefficients for volume ( $\alpha_v$ ) have been combined with earlier results for end-member Na- and K-feldspars,  $\text{Al}_2\text{Si}_2$  feldspars, including anorthite and celsian from the present study, and Sr- and Pb-feldspar from other workers, show essentially constant, and relatively limited, thermal expansion. In the context of structures where the Lowenstein rule requires Al and Si to alternate among tetrahedra, the proximity of bridging Al-O-Si O atoms to divalent neighbors (ranging from 0 to 2) results in Ca-O (or Ba-O) bonds that are especially short. It is suggested that short bonds such as these have a partly covalent character resulting from the requirement for local charge balance. This, in turn, stiffens the structure. For feldspar series with coupled substitution, the change away from a purely divalent M-site occupant gives the substituting (less strongly bonded) monovalent cations increasingly greater influence on thermal expansion. Overall, thermal expansion in the feldspar system is well represented on a plot of  $\alpha_v$  against room-temperature volume ( $V_{\text{RT}}$ ), where one sees a quadrilateral bounded by data for: (1)  $\text{AlSi}_3$  feldspars whose expansion behavior is governed largely by the size of the monovalent alkali-site occupant; (2)  $\text{Al}_2\text{Si}_2$  feldspars whose expansion is uniformly limited by divalent cations having stronger, partially covalent, bonds to bridging Al-O-Si O atoms; and (3,4) plagioclase and Ba-K feldspars where expansion behavior across the series transitions from one control to the other. Overall, the coefficient of thermal expansion in any binary feldspar series is a linear function of  $V_{\text{RT}}$  between the pertinent end-members. This makes it possible to predict the thermal expansion behavior of any feldspar simply from knowledge of its chemical system and room-temperature volume.

**Keywords:** Thermal expansion, feldspars, plagioclase, celsian