

Effect of iron on the compressibility of hydrous ringwoodite

GEERTJE GANSKOW,* TIZIANA BOFFA BALLARAN, AND FALKO LANGENHORST

Bayerisches Geoinstitut, University of Bayreuth, D-95440 Bayreuth, Germany

ABSTRACT

Single crystals of hydrous ferroan ringwoodites with compositions $(\text{Mg}_{0.97}\text{Fe}_{1.00})_{1.97}\text{Si}_{0.98}\text{H}_{0.13}\text{O}_4$ and $(\text{Mg}_{1.21}\text{Fe}_{0.66}^{2+}\text{Fe}_{0.1}^{3+})_{1.97}\text{Si}_{0.97}\text{H}_{0.06}\text{O}_4$ have been synthesized. Their lattice parameters at ambient conditions are $a = 8.1597(6)$ Å and $V = 543.28(13)$ Å³ and $a = 8.1384(3)$ Å and $V = 539.03(7)$ Å³, respectively. The unit-cell lattice parameters were measured at different pressures up to about 9 GPa by means of X-ray single-crystal diffraction. The P - V data were fitted with a second-order Birch-Murnaghan equation of state (K' fixed to the value of 4) refining to the following equation of state parameters: $V_0 = 543.32(7)$ Å³ and $K_{T0} = 186.5(9)$ GPa for $(\text{Mg}_{0.97}\text{Fe}_{1.00})_{1.97}\text{Si}_{0.98}\text{H}_{0.13}\text{O}_4$ and $V_0 = 539.01(5)$ Å³ and $K_{T0} = 184.1(7)$ GPa for $(\text{Mg}_{1.21}\text{Fe}_{0.66}^{2+}\text{Fe}_{0.1}^{3+})_{1.97}\text{Si}_{0.97}\text{H}_{0.06}\text{O}_4$. Structural refinements indicate the presence of significant octahedral vacancies in sample $(\text{Mg}_{1.21}\text{Fe}_{0.66}^{2+}\text{Fe}_{0.1}^{3+})_{1.97}\text{Si}_{0.97}\text{H}_{0.06}\text{O}_4$ due to the oxidation of 0.1 apfu of ferric iron. Correlation between the O-O distances of the octahedral edges and the shift of the OH-stretching frequency suggest that the H incorporation occurs at the octahedral site.

Keywords: Compressibility, hydrous ringwoodite, single crystal, IR spectrum