# HYDROTHERMAL SYNTHESIS OF WAIRAKITE AND CALCIUM-MORDENITE

L. L. Ames and L. B. Sand, University of Utah, Salt Lake City, Utah.

#### ABSTRACT

The zeolites wairakite (CaO·Al $_2$ O $_3$ ·4SiO $_2$ ·2H $_2$ O) and calcium-mordenite (CaO·Al $_2$ O $_3$ ·10SiO $_2$ ·7H $_2$ O) were synthesized during the course of studies in the system lime-aluminasilica-water. The conditions for hydrothermal synthesis of these zeolites, their hydrothermal stabilities, and x-ray data are reported. The significance of these data is discussed, as it applies to the natural occurrence of wairakite and mordenite at Wairakei.

## Introduction

During the course of studies in the system lime-alumina-silica-water, the zeolites wairakite (calcium-analcime) and calcium mordenite (ptilolite) were synthesized. The conditions necessary for syntheses approximate the natural environment found at the occurrence of these two zeolites at Wairakei, New Zealand.

Steiner (1953) has reported on the hydrothermal alteration at Wairakei. Types of rock being altered include tuffaceous sandstones, breccias, vitric tuffs and ignimbrite with the original composition of a plagioclase thyolite. Steiner divides the hydrothermal alteration at Wairakei into three zones characterized mineralogically by: 1) upper zone-clays of the montmorillonite group, 2) middle zone-zeolites, and 3) lower zone-adularia. Wairakite was reported by Steiner in cores from 600 to 2890 feet, constituting 2 to 15 per cent of the altered rock. The pH in the zeolite zone fluids was reported by him to be alkaline, with temperature and pressure ranges of 200 to 250° C. and 55 to 265 atmospheres.

Steiner (1955) also reported the physical and chemical properties of wairakite. Coombs (1955) has reported x-ray diffraction data on wairakite.

### PREVIOUS WORK ON CALCIUM ZEOLITE SYNTHESES

Noll (1936a, b) first attempted to synthesize a calcium-analcime (wairakite). He used hydrated alumina, silica gel, and Ca(OH)<sub>2</sub> in solution in the ratio CaO·Al<sub>2</sub>O<sub>3</sub>·4SiO<sub>2</sub>. This starting material was run at 300° C. and 87 atmospheres for between 15 and 24 hours. Noll stated that the phase formed could not yet be identified. These were the same P-T-time conditions which resulted in his successful synthesis of analcime.

Barrer (1950) attempted to synthesize wairakite by ion-exchange from analcime with limited success.

TABLE 1. CRITICAL HYDROTHERMAL RUNS ON THE CALCIUM COMPOSITIONS

Composition	T° C.	P (atm.)	Time	Phases			
CaO ·Al <sub>2</sub> O <sub>3</sub> ·10SiO <sub>2</sub>	330	1000	7	no crystallization			
,	350		5	mordenite			
	380		5	mordenite			
	395		5	wairakite+cash-I+cristobalite			
	420		4	little crystallization			
	435		3	little crystallization			
	455		4	anorthite+cristobalite			
$CaO \cdot Al_2O_3 \cdot 5SiO_2$	305	1000	3	little crystallization			
	325		4	wairakite+cash-I+cristobalite			
	360		4	wairakite+anorthite			
	400		3	wairakite+anorthite			
	420		4	anorthite			
Ca-mordenite	375	1000	5	mordenite			
(Nova Scotia)							
,	385		5	mordenite+wairakite+cristobalite			
	400		5	quartz+anorthite			

### METHODS OF INVESTIGATION

The pressure reactor vessels used were of the "test-tube" type described by Roy, Roy, and Osborn (1950). Runs were made under water pressures of 1000 atmospheres and temperatures from 200° C. to 560° C. The duration of these runs was from one day to one month.

Starting compositions were made by co-precipitating gels and using nitrates and silicic acid with calcination to 600° C. for 20 minutes. Equivalent results were obtained with both types of starting mixtures.

The phases were identified by x-ray diffraction analysis.

# RESULTS

The critical hydrothermal runs are listed in Table 1.

For comparison, data on the sodium analogues are listed in Table 2. The results on the sodium compositions are in essential agreement with Barrer's work (1948).

TABLE 2. CRITICAL HYDROTHERMAL RUNS ON THE SODIUM MORDENITE COMPOSITION

Composition	T° C.	P	Time (days)	Phases		
Na <sub>2</sub> O·Al <sub>2</sub> O <sub>3</sub> ·10SiO <sub>2</sub>	180	saturated vapor	3	little crystallization		
	200	•	2	mordenite		
	300		1	mordenite		
	330		1	albite+quartz		

Table 3. Lattice Spacings and Visually-Estimated Relative Intensities on X-Ray Diffraction Powder Patterns

Hydrothermally-synthesized wairakite			Hydrothermally-synthesized calcium-mordenite			
d (Å)	I		d (Å)		I	
6.81	4		13.4		3	
5.57	9		10.47		1	
4.83	4		9.10		8	
3.64	3		6.61		8	
3.41	10		5.79		1	
3.21	2		4.95		1	
3.05	1		4.54		5	
2.90	8		4.00		6	
2.784	1		3.82		6	
2.675	4		3.48		10	
2.488	5		3.39		4	
2.414	3		3.22		9	
2.275	1		2.89		2	
2.214	3		2.71		1	
2.115	1		2.56		3	
2.000	1		2.44		1	
1.987	3		2.370		1	
1.856	2		2.268		1	
1.822	1		2.124		1	
1.732	4		2.043		1	
1.706	1		1.955		1	3.
1.680	1		1.885		2	
1.653	1		1.804		1	
1.613	1		1.547		1	
1.586	2		1.530		1	
1.489	1		1.480		1	
1.473	1		1.445		1	
1.438	1		1.380		1	
1.409	3		1.300		1	
1.352	3				-	
1.304	1					
1.279	1					
1.258	2					
1.239	1					
1,217	3					

X-ray diffraction data for the synthetic wairakite and calcium-mordenite are given in Table 3.

### DISCUSSION

Wairakite was not synthesized on composition (CaO·Al<sub>2</sub>O<sub>3</sub>·4SiO<sub>2</sub>). The compositions CaO·Al<sub>2</sub>O<sub>3</sub>·5SiO<sub>2</sub> and CaO·Al<sub>2</sub>O<sub>3</sub>·10SiO<sub>2</sub> yielded

wairakite, in the latter case as a decomposition product of calcium mordenite, while CaO·Al<sub>2</sub>O<sub>3</sub>·4SiO<sub>2</sub> and CaO·Al<sub>2</sub>O<sub>3</sub>·6SiO<sub>2</sub> compositions yielded a new transient phase CASH-I\* through the temperature range of wairakite stability. CaO·Al<sub>2</sub>O<sub>3</sub>·9SiO<sub>2</sub> and CaO·Al<sub>2</sub>O<sub>3</sub>·11SiO<sub>2</sub> compositions did not crystallize through the wairakite stability range with runs up to 6 days in duration. Further, the composition ½Na<sub>2</sub>O·½CaO·Al<sub>2</sub>O<sub>3</sub>·5SiO<sub>2</sub> yielded a cubic rather than a psuedo-cubic x-ray diffraction pattern, indicating that analcime is the stable phase on this composition. These results support the view of Steiner (1955) and Coombs (1955) who suggested very limited isomorphous substitution between analcime and wairakite due to the structural differences in these two supposed end members.

The presence of limited amounts of sodium would tend to lower the temperature of formation of wairakite, but whether limited isomorphous substitution of Na for Ca would lower the temperature of formation of wairakite a significant amount is hypothetical. The lower limit of formation of wairakite of 315° C. is suspect in any case, although the upper stability limit of about  $400^{\circ}$  C. probably is accurate to within  $\pm 10^{\circ}$  C.

The synthesis of mordenite (ptilolite), on the other hand, furnishes a good example of a complete isomorphous series from a pure sodium to pure calcium mordenite. The stability range for the synthesis of sodium mordenite was found to be about 190° to 300° C., essentially the same range as reported by Barrer (2). The calcium mordenite was synthesized from about 340° to 380° C. Intermediate sodium-calcium mordenites were found to have intermediate upper stability limits.

An unusual aspect of this study was the failure to synthesize wairakite on composition (CaO·Al<sub>2</sub>O<sub>3</sub>·4SiO<sub>2</sub>). Several unsuccessful attempts were made to synthesize wairakite from a CaO·Al<sub>2</sub>O<sub>3</sub>·4SiO<sub>2</sub> composition starting material. These included CaO·Al<sub>2</sub>O<sub>3</sub>·4SiO<sub>2</sub> plus various amounts of excess Ca(OH)<sub>2</sub>, variation of the pH from 7 to 12 with the addition of NH<sub>4</sub>OH, and the addition of varying amounts of sodium to the CaO·Al<sub>2</sub>O<sub>3</sub>·4SiO<sub>2</sub> starting material. The presence of excess silica in amounts greater than 0.5 mole and less than 1.5 moles is required for the synthesis of wairakite from the composition CaO·Al<sub>2</sub>O<sub>3</sub>·4SiO<sub>2</sub>. Wairakite also was formed as a decomposition product of natural and synthetic mordenite (CaO·Al<sub>2</sub>O<sub>3</sub>·10SiO<sub>2</sub>·7H<sub>2</sub>O). All of the natural zeolites studied (mordenite, heulandite and three clinoptilolites) initially decompose either to analcime or wairakite.

Steiner (1953) reports that ptilolite (mordenite) is the predominant mineral of the zeolite alteration zone at Wairakei, New Zealand, with some wairakite and heulandite.

 $<sup>\</sup>ast$  Follows nomenclature of Rustum Roy (personal communication) who also has noted this phase.

These laboratory phase studies support the premise that excess silica is required for the formation of wairakite. Such an environment exists at Wairakei in the hydrothermally altered rhyolites. It is possible that wairakite is present at Wairakei as a decomposition product of mordenite, rather than as a primary phase.

# ACKNOWLEDGMENTS

The authors are grateful for the financial support of National Science Foundation Project G-2934 and the University of Utah Research Fund.

#### REFERENCES

- Barrer, R. M. (1950) Ion-exchange and ion-sieve processes in crystalline zeolites: Jour. Chem. Soc., London, 2342-2350.
- Barrer, R. M. (1948) Syntheses and reactions of mordenite: Jour. Chem. Soc., London, 2158-2163.
- Coombs, D. S. (1955) X-ray observations on wairakite and non-cubic analcime: Min. Mag., **30**, no. 230, 699–708.
- Noll, W. (1936a) Synthese von Montmorilloniten: Chemie der Erde, 10, 129-153.
- Noll, W. (1936b) Über die Bildungbedingungen von Kaolin, Montmorillonit, Sericit, Pyrophyllit, und Analcim: Min. Petr. Mitt., 48, 210-247.
- Roy, R., Roy, D. M., AND OSBORN, E. F. (1950) Compositional and stability relationships among the lithium alumino-silicates; eucryptite, spodumene and petalite: J. Am. Ceram. Soc., 33, 152-159.
- STEINER, A. (1953) Hydrothermal rock alteration at Wairakei, New Zealand: *Econ. Geol.*, **48**, 1–13.
- STEINER, A. (1955) Wairakite, the calcium analogue of analcime, a new zeolite mineral: *Min. Mag.*, **30**, no. 230, 691–698.

Manuscript received August 16, 1957