NEW MINERAL NAMES

MICHAEL FLEISCHER

Errata to Index of New Mineral Names

[Am. Mineral. 51, 1247-1357 (1966)]

- p. 1256 should read Arequipite=Bindheimite
- p. 1257 should read Ascharite=Szaibelyite
- p. 1263 should read †Bromyrite=Bromergyrite The formula of callaghanite should be Cu₂Mg₂(CO₃)(OH)₆·2H₂O
- p. 1277 should read Glaubapatite = Moneitte + Apatite
- p. 1278 Haggite should read Häggite
- p. 1279 Hanusite should read Hanušite
- p. 1280 *Högbomite -4H, -5H, etc. should read *Högbomite -4H, -5H, etc. Hollingworthite should read *Hollingworthite
- p. 1284 under Jalpaite, the formula should be Ag₃CuS₂ Janosite should read Janošite
- p. 1285 Kasparite should read Kašparite
- p. 1287 Insert new entry

Laubmannite, $Fe_3^{+2}Fe_6^{+3}(PO_4)_4(OH)_{12}$ 34, 513-540

- p. 1288 Lemnasite should read Lemnäsite
- p. 1297 *Nasinite should read *Nasinite
- p. 1299 under Osumilite, insert (before Mg in the formula)
- p. 1309 ‡Siderose should read †Siderose
- p. 1310 Sinnerite should read *Sinnerite
- p. 1324 Wurtzite-4H to -21R should not be in bold face
- p. 1331 under Phosphates-add Laubmannite
- p. 1337 Under As, after the word Arsenates, insert "and Arsenites"
- p. 1339 Delete Callaghanite
- p. 1340 Insert Laubmannite
- p. 1344 Insert Laubmannite
- p. 1350 The heading Nd should read Nb Under Nb, delete Cerianite

Mckinstryite, Mackinstryite

Brian J. Skinner, John L. Jambor, and Malcolm Ross (1966). Mckinstryite, a new copper-silver sulfide. *Econ. Geol.* **61**, 1383-1389.

X-ray fluorescence analysis on 200 mg. by H. J. Rose, Jr. and F. Cuttitta gave Cu 24.9, Ag 6.00, S. 15.1, sum 100.0%, corresponding to Cu_{0.82}Ag_{1.18}S. The composition of the synthetic compound had been established as Cu_{0.8}Ag_{1.2}S by Djurle, *Acta Chem. Scand.* 12, 1427–1436 (1958) and Skinner, *Econ. Geol.* 61, 1–26 (1966). Semiquantitative spectrographic analysis by H. W. Worthing showed also Pb 0.15, Fe 0.03, Ca 0.05, Mg 0.005% and (in ppm) Co 30, Ti 2, Mn 2, Ba 3, Cr 2, Ni 5, Sn 3, V 1. The thermal study of synthetic material showed it to be transformed at 94.9±1.5° to an intergrowth of jalpaite with a hexagonal phase of composition Cu_{0.96}Ag_{1.04}S, which in turn was transformed into a single-phase cubic compound above 139±10°. Etch reactions are given; they are very similar to those of stromeyerite.

Indexed x-ray powder data are given (35 lines). The strongest lines are 2.606 (10) (511, 350), 2.070 (7) (413, 243), 3.508 (6) (400), 3.062 (6) (150), 2.862 (6) (250), 1.948 (5) (641, 004). Precession X-ray study shows the mineral to be orthorhombic, space group Pnam or $Pna2_1$, cell edges refined from the powder data are a 14.043 \pm 0.005, b 15.677 \pm 0.006, c 7.803 \pm 0.003 Å. Z=32.

The mineral is steel-gray on fresh surfaces, tarnishing to dark gray or black. Streak dark gray. One cleavage, poorly developed, fracture subconchoidal. G. (av. of 6) 6.61 ± 0.03 . Talmage hardness B. In reflected light the color is light grayish-white, whiter with a slightly higher reflectivity than stromeyerite. Strongly anisotropic, with gray, pale grayish-blue, and light tan colors. Anisotropism less than that of stromeyerite, stronger than that of jalpaite. No twinning was noted.

The mineral occurs in a specimen collected in 1907 at the Foster Mine, Cobalt, Ontario, as masses of intergrown crystals 0.2 to 3 mm. in diameter. Associated minerals include chalcopyrite, stromeyerite, gangue calcite and actinolite, and minor silver and arsenopyrite.

The name is for Hugh Exton McKinstry, 1896–1961, Professor of Economic Geology at Harvard University.

The mineral was approved before publication by the Commission on New Minerals and Mineral Names, IMA, with the suggestion that the spelling be changed to "mackinstryite" to avoid possible confusion in indexing. The authors state "The spelling suggestion has not been accepted because we believe the possible confusions in indexing are less serious than the disservice to the scientist whose name is so casually changed. Because mineral names are not capitalized, however, the 'k'should also appear in lower case."