

MINERALOGICAL NOTES

NEW DATA ON GUILDITE

R. B. LAUGHON, *Geology Branch, N.A.S.A., Manned Spacecraft Center, Houston, Texas 77058*

Guildite is monoclinic with $a=9.786$, $b=7.134$, $c=7.263$ and $\beta=105^\circ 17'$. Systematic extinctions show the space group to be $P2_1/m$ or $P2_1$. Available evidence points to a probable formula of $2[\text{CuFe}(\text{SO}_4)_2(\text{OH}) \cdot 4\text{H}_2\text{O}]$.

INTRODUCTION

Guildite is one of a number of secondary minerals formed as a result of a mine fire at Jerome, Arizona. It was originally described by Lausen (1928) and apparently has not been found at any other locality in the succeeding years. Some inconsistencies between the original description and the present work dictate that a re-definition is in order. A complete structural determination is in progress.

TABLE 1. PHYSICAL CONSTANTS FOR GUILDITE

	Lausen (1928)	This Study
Cleavage	(001) (100) } Perfect	same
Color	Honey yellow to deep chestnut brown	same
Streak	Pale canary yellow	same
Hardness	2.5	same
ρ (meas.)	2.725	2.695 ± 0.01
Opt.	Biaxial (+)	same
α	1.623 ± 0.005	1.622 ± 0.001^a
β	1.630 ± 0.005	1.628 ± 0.001^a
γ	1.684 ± 0.005	1.681 ± 0.001^a
Birefringence	0.061	0.059 ± 0.002
Pleochroism	X=pale yellow Y=pale yellow Z=greenish yellow	same
$2V_z$	—	$62 \pm 2^\circ$ meas.
a	—	$9.786 \pm 0.002 \text{ \AA}$
b	—	$7.134 \pm 0.001 \text{ \AA}$
c	—	$7.263 \pm 0.001 \text{ \AA}$
β	$105^\circ 17'$	$105^\circ 17'$ (morph.) $105^\circ 18 \pm 1'$ (X-ray)
Volume	—	489.08 \AA^3
Z	—	2
Axial Ratio	1.037:1:1.407 (morph.)	1.018:1:1.372 (X-ray)

^a Refractive indices determined using white light filtered through filter of 5930 Å.

EXPERIMENTAL

Physical properties are tabulated in Table 1 and compared to Lausen's original description (1928). Optics were determined using spindle stage techniques. The specific gravity was determined from multiple weighings of a number of samples on a Berman density balance.

Zero, first, and second level Weissenberg photographs as well as zero level Precession

TABLE 2. X-RAY POWDER DATA FOR GUILDITE

$d_{(\text{meas.})}$	$d_{(\text{calc.})}$	hkl	I	$d_{(\text{meas.})}$	$d_{(\text{calc.})}$	hkl	I
9.46	9.44	100	35	2.549	2.546	31 $\bar{2}$	vw
6.50	6.51	10 $\bar{1}$	7	2.502	2.502	221	vw
4.998	4.999	011	27	2.355	2.354	20 $\bar{3}$	10
4.806	4.807	11 $\bar{1}$	7	2.238	2.241	410	7
4.720	4.720	200	7	2.166	2.169 2.165	30 $\bar{3}$ 32 $\bar{2}$	4
4.493	4.503	20 $\bar{1}$	3	2.076	2.077 2.075	401 31 $\bar{3}$	12
4.107	4.109	111	7	2.001	2.003 2.000	12 $\bar{3}$ 31 $\bar{2}$	vw
3.812	3.807	21 $\bar{1}$	vw	1.966	1.968 1.965	032 22 $\bar{3}$	4
3.606	3.609	10 $\bar{2}$	20	1.887	1.888 1.887	500 51 $\bar{1}$	3
3.565	3.567	020	vw	1.806	1.810 1.805	10 $\bar{4}$ 20 $\bar{4}$	3
3.502	3.503	002	7	1.784	1.784	040	3
3.336	3.337	120	3	1.703			3
3.144	3.148	211	100	1.677			vw
3.037	3.034	102	5	1.574			4
2.961	2.960	21 $\bar{2}$	4	1.561			vw
2.909	2.909	121	11				
2.878	2.879	310	8				
2.975	2.976	22 $\bar{1}$	3				
2.622	2.624	301	4				

TABLE 3. CHEMICAL ANALYSES

	Lausen (1928)	Microprobe ^a	Conventional ^b
CuO	15.78%	16. ± 2%	16.4 ± .2%
FeO	1.49	—	—
Fe ₂ O ₃	19.12	22. ± 2 ^c	21.8 ± .2 ^c
Na ₂ O	1.23	Not detected	<0.005
SO ₃	39.68	41. ± 4	38.6 ± .4
Al ₂ O ₃	2.11	2. ± .2	—
H ₂ O	22.15	—	21.7 ± .2
Total	101.56		98.5

^a Correction for absorption, fluorescence and atomic number were carried out using the method described by Smith (1965) utilizing a computer program written by Rucklidge at the University of Toronto in 1967. Values are reported only to the nearest percent since stoichiometric proportions were assumed for the standards.

^b Analyses for copper, iron, and sodium by atomic absorption spectrophotometry; K. V. Rodgers, analyst. Analyses for iron and sulfate by "wet" techniques and water by C.E.C. Moisture Analyzer; R. E. McInturff, analyst.

^c Total iron reported as Fe₂O₃.

photographs were made on each crystallographic axis using two small cleavage fragments. Systematic extinctions of the type $0k0$ with k odd establish the space group as either $P2_1/m$ or $P2_1$. Morphology indicates that the former is correct.

Lattice parameters were derived from a least squares refinement of measurements made on a Picker FACS-1 automated diffractometer. These values, as well as the axial ratio, are also given in Table 1 and the latter is compared to the value obtained by Lausen (1928). The a and c crystallographic axes have been interchanged from Lausen's orientation, in keeping with modern convention.

Powder data (Table 2) were collected with a 114.6 mm Debye-Scherrer camera using Mn-filtered Fe radiation with Si as an internal standard. Intensities were obtained by planimetry peaks on a powder diffractometer tracing.

CHEMISTRY

The formula for guildite originally proposed by Lausen (1928) was $3(\text{Cu,Fe})\text{O} \cdot 2(\text{Fe,Al})_2\text{O}_3 \cdot 7\text{SO}_3 \cdot 17\text{H}_2\text{O}$. Written more conventionally, this becomes $(\text{Cu,Fe})_3(\text{Fe,Al})_4\text{S}_7\text{O}_{30} \cdot 17\text{H}_2\text{O}$ or $(\text{Cu,Fe})_3(\text{Fe,Al})_4(\text{SO}_4)_7\text{O}_2 \cdot 17\text{H}_2\text{O}$. This formula would require a cell more than twice the volume of that actually found. Additionally, the space group symmetry requires that there be an even number of all atoms.

Approximate analysis by electron microprobe and more reliable work by more conventional methods failed to detect any gross errors in the original analysis. All results are tabulated in Table 3. With the aid of a computer the present analytical data were compared to the calculated analyses of about 87,000 hypothetical idealized formulae. Only one of these is in reasonable agreement with the chemical information, mea-

sured specific gravity, symmetry requirements of the space group, and measured cell volume. This formula also happens to be charge balanced although this was not a strict requirement of the computer program. The postulated idealized formula is $2[\text{CuFe}(\text{SO}_4)_2(\text{OH}) \cdot 4\text{H}_2\text{O}]$. Ultimate proof of the formula is, of course, the structural determination now in progress.

ACKNOWLEDGEMENTS

This study was originally suggested by M. M. Wood, who is investigating some other members of the Jerome suite of minerals. R. E. Wilcox made several helpful suggestions during the re-examination of the optics and D. S. McKay provided invaluable assistance with the microprobe analysis. J. E. Wainwright made many helpful suggestions. J. W. Anthony provided material for the study from the Mineralogical Museum of the University of Arizona and kindly reviewed the manuscript.

REFERENCES

- LAUSEN, C. (1928) Hydrous sulphates formed under fumerolic conditions at the United Verde mine. *Amer. Mineral.* **13**, 203-229.
- SMITH, J. V. (1965) X-ray-emission microanalysis of rock-forming minerals. I. Experimental techniques. *J. Geol.* **73**, 830-864.

THE AMERICAN MINERALOGIST, VOL. 55, MARCH-APRIL, 1970

CONFIRMATION OF THE MINERAL SPECIES WHERRYITE

W. JOHN McLEAN, *Department of Geology, University of Arizona,
Tucson, Arizona 85721*

ABSTRACT

The unit cell of wherryite is $a=20.82$, $b=5.79$, $c=9.17$ Å, $\beta=91^\circ 17'$; space group $C2$, Cm , or $C2/m$. Wherryite may be related to leadhillite.

INTRODUCTION

Wherryite was described in 1950 by Fahey, Daggett, and Gordon on material from the Mammoth mine, Tiger, Arizona. It was described as light green and as having a fine granular texture. The specific gravity was determined to be 6.45 and the chemical formula was given as $\text{Pb}_4\text{Cu}(\text{CO}_3)(\text{SO}_4)_2(\text{OH}, \text{Cl})_2\text{O}$. The validity of wherryite as a mineral species has been doubted (Strunz, 1966). The present work appears to confirm wherryite as a species distinct from caledonite and leadhillite.

SPECIMENS

The present study made use of three specimens from the Mammoth mine which will be referred to in this paper as specimens nos. 1, 2, and 3. Wherryite occurs on spec. no. 1 (USNM spec. no. 8171) as crystals which vary in color from pale yellow to bright yellowish-