$\label{eq:single-crystal} \begin{array}{l} structure\ refinement\ of\ synthetic\ ^{M4}K-substituted\ potassic\ richterite, \\ K(KCa)Mg_5Si_8O_{22}(OH)_2 \end{array}$

HEXIONG YANG,* JÜRGEN KONZETT, CHARLES T. PREWITT, AND YINGWEI FEI

Geophysical Laboratory and Center for High Pressure Research, Carnegie Institution of Washington, 5251 Broad Branch Road, N.W., Washington, D.C. 20015-1305, U.S.A.

ABSTRACT

The crystal structure of a potassic richterite, K(KCa)Mg₅Si₈O₂₂(OH)₂ synthesized at 15 GPa and 1400 °C, was refined from single-crystal X-ray diffraction data. The unit-cell parameters are: a = 10.1926(5), b = 18.1209(3), c = 5.2736(2) Å, and $\beta = 105.514(5)^{\circ}$. The refinement shows that the M4 site is occupied by K and Ca at a ratio of 1:1 with no site splitting. Entrance of K into the M4 site mainly affects the local environment: the M4-O2, M4-O4, and M4-O6 bond lengths in KK richterite are 3.4, 3.7, and 3.1% longer, respectively, than the corresponding ones in potassium richterite, whereas the M4-O5 distance is 1.2% shorter, giving rise to a more regular M4 polyhedron. Three major structural adjustments allow the M4 site to accommodate large K: a shift of the M4 cation along the two-fold *b* axis, a modification of the double silicate-chain configurations, and relative displacements of the two back-to-back tetrahedral chains. K at the A site is completely ordered at the Am position. The average of eight shortest A-O distances is 0.044 Å longer than that in potassium richterite, despite the A site being fully filled with K in both structures. The unpolarized Raman spectrum displays only one single band at 3735.5 cm⁻¹ in the OH-stretching region.