

## **Thermodynamics of manganese oxides: Effects of particle size and hydration on oxidation-reduction equilibria among hausmannite, bixbyite, and pyrolusite**

**NANCY BIRKNER AND ALEXANDRA NAVROTSKY\***

Peter A. Rock Thermochemistry Laboratory and NEAT ORU and Department of Chemistry, University of California, Davis, California 95616, U.S.A.

### **ABSTRACT**

The surface enthalpies of manganese oxide phases, hausmannite ( $\text{Mn}_3\text{O}_4$ ), bixbyite ( $\text{Mn}_2\text{O}_3$ ), and pyrolusite ( $\text{MnO}_2$ ), were determined using high-temperature oxide melt solution calorimetry in conjunction with water adsorption calorimetry. The energy for the hydrous surface of  $\text{Mn}_3\text{O}_4$  is  $0.96 \pm 0.08 \text{ J/m}^2$ , of  $\text{Mn}_2\text{O}_3$  is  $1.29 \pm 0.10 \text{ J/m}^2$ , and of  $\text{MnO}_2$  is  $1.64 \pm 0.10 \text{ J/m}^2$ . The energy for the anhydrous surface of  $\text{Mn}_3\text{O}_4$  is  $1.62 \pm 0.08 \text{ J/m}^2$ , of  $\text{Mn}_2\text{O}_3$  is  $1.77 \pm 0.10 \text{ J/m}^2$ , and of  $\text{MnO}_2$  is  $2.05 \pm 0.10 \text{ J/m}^2$ . Supporting preliminary findings (Navrotsky et al. 2010), the spinel phase (hausmannite) has a lower surface energy than bixbyite, whereas the latter has a smaller surface energy than pyrolusite. Oxidation-reduction phase equilibria at the nanoscale are shifted to favor the phases of lower surface energy— $\text{Mn}_3\text{O}_4$  relative to  $\text{Mn}_2\text{O}_3$  and  $\text{Mn}_2\text{O}_3$  relative to  $\text{MnO}_2$ . We also report rapidly reversible structural and phase changes associated with water adsorption/desorption for the nanophase manganese oxide assemblages.

**Keywords:** Manganese oxides, nanomaterials, calorimetry, surface energy, surface hydration, phase equilibria