

Charleshatchettite, $\text{CaNb}_4\text{O}_{10}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$, a new mineral from Mont Saint-Hilaire, Québec, Canada: Description, crystal-structure determination, and origin

MONIKA M.M. HARING^{1,*} AND ANDREW M. McDONALD¹

¹Department of Earth Sciences, Laurentian University, Sudbury, Ontario P3E 2C6, Canada

ABSTRACT

Charleshatchettite, $\text{CaNb}_4\text{O}_{10}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$, is a new mineral related to franconite and hochelagaite, discovered on a fracture surface of a nepheline syenite at Mont Saint-Hilaire, Québec, Canada. The mineral occurs in white globules (~0.15–0.20 mm in diameter) composed of radiating crystals with individual crystals having average dimensions of $\sim 0.002 \times 0.010 \times 0.040$ mm. Crystals are euhedral, bladed (flattened on [100]), and are transparent to translucent. The mineral is associated with albite, quartz, muscovite, pyrrhotite, pyrite, ancylite-(Ce), and siderite. Charleshatchettite is inferred to be biaxial (–) with $\alpha' = \sim 1.72(2)$ and $\gamma' = \sim 1.82(2)$. Data from chemical analyses (SEM-EDS, $n = 8$): CaO 7.96 (7.04–8.63), MgO 0.24 (0.08–0.78), Al_2O_3 0.13 (b.d.–0.49), SiO_2 1.04 (0.49–1.88), TiO_2 3.64 (2.45–5.05), Nb_2O_5 68.07 (64.83–71.01), and H_2O (calc) 22.96, total 104.04 wt% gives the average empirical formula: $(\text{Ca}_{1.00}\text{Mg}_{0.04})_{\Sigma 1.04}(\text{Nb}_{3.62}\text{Ti}_{0.32}\text{Si}_{0.12}\text{Al}_{0.02})_{\Sigma 4.08}\text{O}_{10}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$ (based on 20 anions). This is similar to that of hochelagaite ($\text{CaNb}_4\text{O}_{11} \cdot n\text{H}_2\text{O}$), although the two are readily distinguished by their powder X-ray diffraction patterns. Results from single-crystal X-ray diffraction analysis give $a = 21.151(4)$, $b = 6.496(2)$, $c = 12.714(3)$ Å, and $\beta = 103.958(3)^\circ$, space group $C2/c$ (no. 15). The crystal structure, refined to $R = 5.64\%$, contains 1 Ca site, 2 distorted octahedral Nb sites, and 10 O sites. It consists of clusters of four edge-sharing $\text{Nb}(\text{O},\text{OH})_6$ octahedra, linked through shared corners to adjacent clusters, forming layers of $\text{Nb}(\text{O},\text{OH})_6$ octahedra. These alternate along [100] with layers composed of $\text{Ca}(\text{H}_2\text{O})_8$ polyhedra, the two being linked together by H-bonding. Charleshatchettite is a late-stage mineral, interpreted to have developed through the interaction of low- T (<150 °C) aqueous fluids with an alkali-, Nb-rich precursor under slightly reducing conditions and a highly alkaline pH. The precursor mineral(s) is unknown but is considered to have been Nb-dominant, relatively unstable under slightly reducing as well as alkaline conditions, and likely itself would have been a product of near-complete Nb/Ta fractionation due to the paucity of Ta in charleshatchettite. Charleshatchettite is crystallochemically related to Sandia Octahedral Molecular Sieves [SOMS; $\text{Na}_2\text{Nb}_{2-x}\text{M}_x\text{O}_{6-x}(\text{OH})_x \cdot \text{H}_2\text{O}$ with $M = \text{Ti}, \text{Zr}, \text{Hf}$], a group of synthetic compounds with strong ion exchange capabilities.

Keywords: New mineral, charleshatchettite, Mont Saint-Hilaire, SOMS, hochelagaite, franconite, Nb/Ta fractionation, crystal structure