Sassi et al. Supplementary Info

AM-10-035




Figure 5. XRPD diagram of a phengite concentrate (99% purity) of the sample CHIVE-5 (operating conditions: 40 kV and 30 mA; $54\text{--}64 2\theta$ range; step scan mode, with step width increments of $0.02^{\circ} 2\theta$, and step counting time of 2 s).