

Lakargiite CaZrO₃: A new mineral of the perovskite group from the North Caucasus, Kabardino-Balkaria, Russia

**EVGENY V. GALUSKIN,^{1,*} VIKTOR M. GAZEEV,² THOMAS ARMBRUSTER,³ ALEKSANDER E. ZADOV,⁴
IRINA O. GALUSKINA,¹ NIKOLAI N. PERTSEV,² PIOTR DZIERŻANOWSKI,⁵ MILEN KADIYSKI,³
ANATOLY G. GURBANOV,² ROMAN WRZALIK,⁶ AND ANTONI WINIARSKI⁶**

¹Faculty of Earth Sciences, Department of Geochemistry, Mineralogy, and Petrography, University of Silesia, Będzińska 60, 41-200 Sosnowiec, Poland

²Institute of Geology of Ore Deposits, Geochemistry, Mineralogy, and Petrography (IGEM), Russian Academy of Sciences, Staromonetny 35, 119017 Moscow, Russia

³Mineralogical Crystallography, Institute of Geological Sciences, University of Bern, Freiestrasse 3, CH-3012 Bern, Switzerland

⁴OOO NPP TEPLOHIM, Dmitrovskoye av., 71, 127238 Moscow, Russia

⁵Institute of Geochemistry, Mineralogy, and Petrology, Warsaw University, al. Żwirki i Wigury 93, 02-089 Warszawa, Poland

⁶August Chelkowski Institute of Physics, University of Silesia, Uniwersytecka 4, 40-007 Katowice, Poland

ABSTRACT

Lakargiite CaZrO₃—the zirconium analog of perovskite [*Pbnm*, *a* = 5.556(1), *b* = 5.715(1), *c* = 7.960(1) Å, *V* 252.7(1) Å³, *Z* = 4]—was discovered as an accessory mineral in high-temperature skarns in carbonate-silicate rocks occurring as xenoliths in ignimbrites of the Upper-Chegem (Verkhniy Chegem) volcanic structure, the North Caucasus, Kabardino-Balkaria, Russia. Lakargiite forms pseudo-cubic crystals up to 30–35 μm in size and aggregates up to 200 μm. Lakargiite is associated with spurrite, larnite, calcio-olivine, calcite, cuspidine, rondorfite, reinhardbraunsite, wadalite, perovskite, and minerals of the ellestadite group. The new perovskite mineral belongs to the ternary solid solution CaZrO₃-CaTiO₃-CaSnO₃ with a maximum CaZrO₃ content of ca. 93%, maximum CaTiO₃ content of 22%, and maximum CaSnO₃ content of 20%. Significant impurities are Sc, Cr, Fe, Ce, La, Hf, Nb, U, and Th. Raman spectra of lakargiite are similar to those of the synthetic phase Ca(Zr,Ti)O₃ with strong bands at 352, 437, 446, 554, and 748 cm⁻¹. Lakargiite crystallized under sanidinite-facies conditions of contact metamorphism characterized by very high temperatures and low pressures.

Keywords: Lakargiite, perovskite group, solid solution, CaZrO₃, CaSnO₃, Raman spectroscopy, skarn, Caucasus