

LETTER

The elastic tensor of monoclinic alkali feldspars

NAËMI WAESLMANN^{1,*}, J. MICHAEL BROWN¹, ROSS J. ANGEL², NANCY ROSS³, JING ZHAO³, AND WERNER KAMINSKY⁴

¹Department of Earth and Space Sciences, University of Washington, 4000 15th Avenue NE, Seattle, Washington 98195-1310, U.S.A.

²Department of Geosciences, University of Padova, Via G. Gradenigo 6, I-35131 Padova, Italy

³Department of Geosciences, Virginia Tech, 4044 Derring Hall (0420), Blacksburg, Virginia 24061, U.S.A.

⁴Department of Chemistry, University of Washington, 36 Bagley Hall, Seattle, Washington 98195-1700, U.S.A.

ABSTRACT

The full elastic tensors of two K-rich monoclinic alkali feldspars, Or₈₃Ab₁₅ sanidine and Or₉₃Ab₇ orthoclase, have been determined by using the Impulse Stimulated Light Scattering technique to measure surface acoustic wave velocities. The new data confirm that alkali feldspars exhibit extreme elastic anisotropy, so the bounds of their isotropic average properties span a wide range. The measured adiabatic moduli are, for Or₈₃Ab₁₅ and Or₉₃Ab₇, respectively, $K_{\text{Reuss}} = 54.7(7)$, $54.5(5)$ GPa; $K_{\text{Voigt}} = 62.9(1.1)$, $64.4(0.6)$ GPa; $G_{\text{Reuss}} = 24.1(1)$, $24.5(1)$ GPa; and $G_{\text{Voigt}} = 36.1(5)$, $36.1(7)$ GPa. The small differences in moduli between the samples suggests that variations in composition and in state of Al, Si order only have minor effects on the average elastic properties of K-rich feldspars. The new measurements confirm that the earliest determinations of elastic wave velocities of alkali feldspars, widely used to calculate wave velocities in rocks, resulted in velocities systematically and significantly too slow by 10% or more.

Keywords: Alkali feldspar, elastic tensor, impulse stimulated light scattering