

## **$^{222}\text{Rn}$ and $^{220}\text{Rn}$ emanations from powdered samples of samarskite as a function of annealing temperature**

**DARIUSZ MALCZEWSKI<sup>1,\*</sup> AND MARIA DZIURWICZ<sup>1</sup>**

<sup>1</sup>Faculty of Earth Sciences, University of Silesia, Bedzinska 60, 41-200 Sosnowiec, Poland

### **ABSTRACT**

Emanation coefficients for radon ( $^{222}\text{Rn}$ ) and thoron ( $^{220}\text{Rn}$ ) were measured from fully metamict samarskite collected from Centennial Cone after 1 h and 24 h annealing in argon from 473 to 1373 K. For the 1 h annealing run,  $^{222}\text{Rn}$  emanation coefficients ranged from  $5 \times 10^{-6}$  to  $2.1 \times 10^{-5}$  %, while  $^{220}\text{Rn}$  coefficients varied from  $6.3 \times 10^{-3}$  to  $2 \times 10^{-2}$  %. For the 24 h annealing run,  $^{222}\text{Rn}$  coefficients ranged from  $5.8 \times 10^{-6}$  to  $2.3 \times 10^{-5}$  %, while  $^{220}\text{Rn}$  coefficients varied from  $4.1 \times 10^{-3}$  to  $1.5 \times 10^{-2}$  %. The  $^{222}\text{Rn}$  and  $^{220}\text{Rn}$  emanation coefficients vs. annealing temperature data can be described by an exponentially decreasing sinusoidal function. Both  $^{222}\text{Rn}$  and  $^{220}\text{Rn}$  emanation coefficient values after annealing considerably exceeded those measured from an unheated powder reference sample and from the original samarskite sample.

**Keywords:** Samarskite, radon emanations, thoron emanations, recrystallization, Centennial Cone,  $^{222}\text{Rn}$ ,  $^{220}\text{Rn}$