

Determination of high-pressure phase equilibria of Fe₂O₃ using the Kawai-type apparatus equipped with sintered diamond anvils

EIJI ITO,^{1,*} HIROSHI FUKUI,^{1,2} TOMOO KATSURA,¹ DAISUKE YAMAZAKI,¹ TAKASHI YOSHINO,¹ YOSHITAKA AIZAWA,¹ ATSUSHI KUBO,^{1,3} SHO YOKOSHI,¹ KAZUYOKI KAWABE,¹ SHUANGMENG ZHAI,¹ ANTON SHATZKIY,¹ MAKI OKUBE,^{1,4} AKIFUMI NOZAWA,⁵ AND KEN-ICHI FUNAKOSHI⁵

¹Institute for Study of the Earth's Interior, Okayama University, Misasa, Tottori-ken 682-0193, Japan

²RIKEN Harima Institute, 1-1-1, Kouto, Sayo-cho, Sayo-gun, Hyogo 679-5148, Japan

³Center for Advanced Radiation Sources, The University of Chicago, Argonne, Illinois 60439, U.S.A.

⁴Materials and Structures Laboratory, Tokyo Institute of Technology, Yokohama, Kanagawa 226-8503, Japan

⁵Japan Synchrotron Radiation Research Institute, Hyogo-ken 678-5198, Japan

ABSTRACT

Phase equilibria of Fe₂O₃ have been studied up to 58 GPa and 1400 K using the Kawai-type multi anvil apparatus equipped with sintered diamond anvils. Identification of phases and pressure determination has been carried out by means of in situ X-ray observation using synchrotron radiation at SPring-8. Hematite (phase I) successively transforms to the Rh₂O₃(II)-type structure (phase II) and then to an orthorhombic structure (phase III) with increasing pressure. The transformations of hematite into high-pressure phases have been observed only at temperatures higher than 500 K, which is not concordant with previous results obtained by using the diamond anvil cell. Volume changes accompanied by the I-II and II-III transformations are calculated to be -2.8 and -5.0%, respectively. The phase boundary between I and II phases and that between II and III have been proposed to be P (GPa) = -0.015 T (K) + 44.2 and P (GPa) = -0.005 T (K) + 48.7, respectively. Possible correlation between a Mott transition and the phase stabilities may be concealed at room temperature due to slow reaction kinetics of the structural transformations.

Keywords: High-pressure phase equilibria, Fe₂O₃, Kawai-cell, sintered diamond, in situ X-ray observation