

Stability of uranium (VI) peroxide hydrates under ionizing radiation

**ALEXANDRA REY,¹ SATOSHI UTSUNOMIYA,^{2,*} JAVIER GIMÉNEZ,¹ IGNASI CASAS,¹ JOAN DE PABLO,^{1,3}
AND RODNEY C. EWING²**

¹Department of Chemical Engineering, Universitat Politècnica de Catalunya (UPC), 08028 Barcelona, Spain

²Department of Geological Sciences, University of Michigan, Michigan 48109-1005, U.S.A.

³Centre Tecnològic, Manresa (CTM), 08242 Manresa, Barcelona, Spain

ABSTRACT

The uranyl peroxide, studtite ($\text{UO}_4 \cdot 4\text{H}_2\text{O}$, $C2/c$, $Z = 4$), is expected to form as a consequence of alpha radiolysis of water in contact with spent nuclear fuel (SNF) in a geologic repository. Investigation of its stability is, therefore, of critical importance because secondary U(VI) phases may incorporate trace amounts of radionuclides and thus retard their mobility away from a repository site. To examine the effect of ionizing radiation on uranyl peroxides, electron-beam irradiation experiments have been conducted on two synthetic uranyl peroxides: studtite and metastudtite ($\text{UO}_4 \cdot 2\text{H}_2\text{O}$, $Immm$, $Z = 2$). All experiments were done using a transmission electron microscope (TEM) with an acceleration voltage of 200 kV at room temperature. The fluence required to completely amorphize studtite was $0.51\text{--}1.54 \times 10^{17}$ e/cm², which is equivalent to an absorbed dose of $0.73\text{--}1.43 \times 10^7$ Gy. Metastudtite becomes amorphous at a higher absorbed dose (1.31×10^7 Gy) than studtite, most likely because it contains fewer water molecules in its structure. These uranyl peroxides partially amorphize at doses that are one-tenth of the dose required for complete amorphization. With continued irradiation, uraninite nanocrystals form that are a few nanometers in diameter, at $4\text{--}20 \times 10^{10}$ Gy. In a geologic repository, for spent nuclear fuel, the estimated absorbed doses due to ionizing radiation may be as high as $10^8\text{--}10^{11}$ Gy after 10^6 years. This is well in excess of doses in the laboratory experiments that caused the uranyl peroxides to become amorphous and decompose.

Keywords: Ionizing radiation, TEM, uranyl peroxide, amorphization